Interzinc Aerosol

Primers

Aerosol for Underwater Metals



PRODUCT DESCRIPTION

Interzinc Aerosol is an underwater anti-corrosive metallic protector specially formulated in a convenient, easy to use aerosol. It features superior adhesion to properly prepared underwater metals including stainless steel, aluminum, lead, steel and bronze. Interzinc Aerosol defends against corrosion for running gear such as shafts, struts, rudders and trim tabs. The fast-drying formula dries smooth and creates a hard durable surface. Interzinc Aerosol spray applies effortlessly providing corrosion protection for all your underwater running gears.

PRODUCT INFORMATION

Color YPB351-Gray

Finish Matt

Specific Gravity 1.148 g/L average Volume Solids 13.4% average **Typical Shelf Life** 2 years

VOC (As Supplied) 568 g/L average

Unit Size 16 fl oz

DRYING/OVERCOATING INFORMATION

DITTINO/OVERODATINO INI ONIMATION					
	Drying				
	41°F (5°C)	59°F (15°C)	77°F (25°C)	95°F (35°C)	
Immersion	14 hrs	12 hrs	10 hrs	8 hrs	
Touch Dry [ISO]	30 mins	15 mins	5 mins	5 mins	

Note: Max. Immersion Times are as follows: 5-35°C - 6 months

Overcoating

Substrate Temperature

41°F (5°C) 77°F (25°C) 95°F (35°C) 59°F (15°C) Min Max Overcoated By

APPLICATION AND USE

Preparation BARE METAL: Degrease by wiping with a rag soaked in Fiberglass Solvent Wash 202. Gritblast to near white metal

> surface. If gritblasting is not possible, grind the metal surface with 24-36 grit abrasive discs to a uniform, clean, bright metal surface with 2-3 mils (50-75 microns) anchor pattern. Remove sanding residue with a brush, broom, clean air line

or vacuum. Immediately apply the first coat of Interzinc Aerosol.

PREVIOUSLY PAINTED SURFACES: Remove previously painted surface. Follow Bare Metal instructions above.

Method Shake can well, listening for mixing ball. Continue shaking for at least 1 minute. Hold can 12-16 inches from the unit when

applying the paint. Apply 2-3 coats as needed. Between coats turn can upside and spray until the spray is clear to clean

the nozzle

Some Important Points To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. Product

temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/41°F and

maximum 35°C/95°F. Substrate temperature should be minimum 10°C/50°F and maximum 35°C/95°F.

Compatibility/Substrates

Interzinc Aerosol should be applied to bare metals free of debris or old coating. 1-3 as required.

Number of Coats Coverage

One can of InterZinc will cover 5.25 square feet (theoretical). Approximately 1.5-2 cans of InterZinc will be needed for

the running gear on a typical 30' boat.

Recommended DFT per coat

1-2 mils (25-50 microns)

Application Methods Aerosol

TRANSPORTATION.STORAGE AND SAFETY INFORMATION

Storage GENERAL:

> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interzinc Aerosol to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

Please refer to your local representative or visit www.interlux.com for further information

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019



Interzinc Aerosol

Primers

Aerosol for Underwater Metals



TRANSPORTATION:

The product should be kept in securely closed containers during transport and storage.

Safety GENERAL

Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL:

Do not discard tins or pour paint into water couses, use the facilities provided. It it best to allow paints to harden before disposal. Remainders of Interzinc Aerosol cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.